

## TECAFLON PTFE CM XP79 black - Stock Shapes (rods, plates, tubes)

Chemical Designation
PTFE (Polytetrafluorethylene)

Colour black

*Density* 2.02 g/cm<sup>3</sup>

Main features

broad chemical compatibility
high pressure resistance
high thermal and mechanical capacity

Target Industries

Date: 2022/08/04

chemical plant engineering flow management oil and gas industry

| Mechanical properties                 | parameter         | value   | unit      | norm        | comment |
|---------------------------------------|-------------------|---------|-----------|-------------|---------|
| Modulus of elasticity (tensile test)  | @73°F             | 210,000 | psi       | ASTM D 638  |         |
| Tensile strength at break             | @73°F             | 1,900   | psi       | ASTM D 638  |         |
| Elongation at break (tensile test)    | @73°F             | 180     | %         | ASTM D 638  |         |
| Flexural strength                     | @73°F             | 2,950   | psi       | ASTM D 790  |         |
| Modulus of elasticity (flexural test) | @73°F             | 198,000 | psi       | ASTM D 790  |         |
| Compression strength                  | @73°F; 10% strain | 3,900   | psi       | ASTM D 695  |         |
| Compression strength                  | @73°F; 1% strain  | 1,780   | psi       | ASTM D 695  |         |
| Compression modulus                   | @73°F             | 73,500  | psi       | ASTM D 695  |         |
| Notched impact strength (Izod)        | @73°F             | 1.77    | ft-lbs/in | ASTM D 256  |         |
| Shore hardness                        | D Scale           | 68      |           | ASTM D 2240 |         |

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters 365 Meadowlands Boulevard Washington, PA 15301, USA Phone 800-243-3221 Sales Phone 800-869-4029 Technical Fax 724-746-9209 sales@ensingerusa.com Version: A0