

TECATRON PPS CM CF30 black (XP85) - Stock Shapes (rods, plates, tubes)

Chemical Designation

PPS (Polyphenylsulfide)

Colour

black

Density

1.47 g/cm³

Fillers

30% carbon fibres

Main features

good chemical resistance
excellent wear properties
very good bearing and wear properties

Target Industries

oil and gas industry
others

Mechanical properties	parameter	value	unit	norm	comment
Modulus of elasticity (tensile test)		1,200,000	psi	ASTM D 638	
Tensile strength at break		12,000	psi	ASTM D 638	
Elongation at break (tensile test)		1.76	%	ASTM D 638	
Flexural strength		20,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)		1,300,000	psi	ASTM D 790	
Compression strength	Max Load	26,000	psi	ASTM D 695	
Compression strength	@ 10%	23,000	psi	ASTM D 695	
Compression strength	@ 1%	7,000	psi	ASTM D 695	
Compression modulus	Secant @ 0.5% strain	885,000	psi	ASTM D 695	
Compression modulus		680,000	psi	ASTM D 695	
Notched impact strength (Izod)		.74	ft-lbs/in	ASTM D 256	
Shore hardness	D Scale	91		ASTM D 2240	

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensingerusa.com

Date: 2022/07/22

Version: