

## TECAPEEK CM GF25 (XP-90) - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PEEK (Polyetheretherketone)

### Colour

beige

### Density

1.52 g/cm<sup>3</sup>

### Fillers

glass fibres

### Main features

excellent chemical resistance  
very good bearing and wear properties  
excellent strength

### Target Industries

chemical plant engineering  
oil and gas industry

<i>Mechanical properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Tensile strength	73°F	15,100	psi	ASTM D 638	(1) Units = Rockwell M
Elongation at break (tensile test)	73°F	2.8	%	ASTM D 638	
Flexural strength	73°F	21,500	psi	ASTM D 790	
Modulus of elasticity (flexural test)	73°F	850,000	psi	ASTM D 790	
Rockwell hardness	73°F	105		ASTM D 785	1)
<i>Thermal properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Melting temperature		649	°F	-	

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com).

Ensinger Inc. Headquarters  
365 Meadowlands Boulevard  
Washington, PA 15301, USA

Phone 800-243-3221 Sales  
Phone 800-869-4029 Technical  
Fax 724-746-9209  
[sales@ensingerusa.com](mailto:sales@ensingerusa.com)

Date: 2016/11/10

Version: